

L3 ANSWER 51 OF 54 CAPLUS COPYRIGHT 2003 ACS
 AN 1975:113100 CAPLUS
 DN 82:113100
 TI **Odorless** latexes for **carpet** backing
 IN Watanabe, Shunsuke; Okoshi, Noboru
 PA Dainippon Ink and Chemicals, Inc., Japan
 SC Jpn. Kokai Tokkyo Koho, 4 pp.
 CODEN: JKXXAF
 DT Patent
 LA Japanese
 FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 49099545	A2	19740920	JP 1973-9551	19730124 <--
PRAI	JP 1973-9551		19730124		

AB **Odorless** latexes contained activated carbon [7440-44-0]. For example, a composition from 50% carboxylated SBR latex 100, a 20% nonionic surfactant solution 0.5, 20% Ca pyrophosphate 0.75, CaCO₃ 200, antioxidant 1, 50% ZnO dispersion 2, activated carbon 8, TiO₂ 0.5, defoamer 0.1, antiseptic 0.02, and 35% aqueous Na polyacrylate 1.5 parts was coated to 1.5 kg/cm² on a tufted **carpet**, overlaid with jute, and heated at 140° for 10 min to give **odorless** backing.

BEST AVAILABLE COPY